

### Product description

Matt polyurethane material for heat transfer applications.

**Thickness** : 50-60 microns (USA : 2,2-2,4 mil).

**Carrier** : self-adhesive and transparent polyester.

**Norm** : Oekotex label.

### Suitable for

Cotton, polyester, acrylic and similar fibres.

### Application advises

- 1) Cut the material in reverse with regular flex blade.
- 2) Weed the excess material.
- 3) Heat press the image on the garment with its polyester carrier protected by a silicone paper at 150-180°C (USA : 300-360°F) – 15-20 seconds – medium pressure.
- 4) Peel the carrier off when cold.

### Maintenance

Always respect the instructions mentioned on garments.  
After heat pressing, wait 24 hours before the first wash.

**Washing** : 80°C (USA : 180°F) max. inside out - without bleach or any aggressive washing products.

**Dried cleaning** : yes

**Ironing** : backside

**Storage of the roll** : vertically, one year in a dry room, 15-30°C (USA : 60-85°F), protected from sunlight.

### Caution

Those recommendations are based on our own experiences.  
We always recommend making trials before starting standard production.

May 2009